

# PRODUCT DATA SHEET



## AGILENE30GF-IM

### Product Description

PBT - 30% Glass reinforced, Impact Modified .

### Product Applications

Electronics & Electrical , Automotive etc.

### General

Forms - Pellets  
Appearance/Color - White/Natural  
Processing Method - Injection molding

Physical	Typical Value	Unit	Test Method
Specific Gravity	1.48	-	ASTM D -792

Mechanical	Typical Value	Unit	Test Method
Tensile Strength	110	Mpa	ASTM D-638
Elongation at Yield	3	%	ASTM D-638
Elongation at Break	3.5	%	ASTM D-638
Flexural strength	185	MPa	ASTM D-790
Flexural Modulus	8500	MPa	ASTM D-790
Notched Izod Impact strength	10.5	Kg.cm/cm	ASTM D-256A



# PRODUCT DATA SHEET

# AGILENE30GF-IM

## Drying conditions

It is recommended to pre dry PBT granules at 90-100 °C for 3-4 Hrs.  
Moisture content after drying should be <0.2%.  
Avoid sudden cooling of dry pellet.

## Injection Molding conditions ( ° C )

Feed Zone	Centre	Nozzle	Melt	Mould
235-240	250-260	250-260	240-250	90-110

## Note

All Properties measured at 23 Deg. / 50% RH on dry-as-moulded test specimens. Only typical data for material selection purposes only. Users have to establish material suitability. The information & data presented herein are to the best of our knowledge. No warranty or guarantee expressed or implied is made regarding performance. The information and data are subject to change without prior intimation based on research and development work undertaken by the company.

### Plant

C-10/1,MIDC,AkkalkotRoad - 413006  
Solapur,Maharashtra,India

### Corporate Office

510 "A" Wing Kohinoor City Commercial – I, Kiro Road,  
Off . L.B .S Marg,Kurla (W) Mumbai - 400070 ,India

Rev no:01

