

## STANDARD SPECIFICATIONS SHEET

Technical Name	<b>HIGH TENSILE NATURAL RECLAIM</b>				
Commercial Name	Testing Methods	GRP NRF90	GRP NRF75	GRP NRF65	GRP NRM60

### TECHNICAL SPECIFICATIONS

Ash %	ISO 247	7 ± 2	7 ± 2	7 ± 2	7 ± 2
Carbon Black %	ISO 1408	28 ± 3	28 ± 3	28 ± 3	28 ± 3
Acetone Extract %	ISO 1407	14.6 ± 2	14.6 ± 2	14.6 ± 2	14.6 ± 2
Volatile Matter %	ISO 248	1 Max.	1 Max.	1 Max.	1 Max.
RHC by Diff. %	By Difference	48 Min.	48 Min.	48 Min.	48 Min.
Sp. Gravity	ISO 2781	1.13 ± 0.02	1.13 ± 0.02	1.13 ± 0.02	1.13 ± 0.02
Tensile Strength (Kg/Cm <sup>2</sup> )	ISO 37, ISO/DTS 16095	90 Min.	75 Min.	65 Min.	60 Min.
Elongation at Break %	ISO 37, ISO/DTS 16095	270 Min.	250 Min.	230 Min.	230 Min.
Massed Mooney Viscosity, ML (1+4) at 100°C	ASTM D1646	35 - 60	35 - 60	35 - 60	35 - 60
Hardness (Shore A)	ISO 7619	59 ± 3	59 ± 3	59 ± 3	59 ± 3

### PHYSICAL SPECIFICATIONS

Grain Size	Visual	Fine	Fine	Fine	Medium
Sheet Thickness	Visual	20 mm Max.	20 mm Max.	20 mm Max.	20 mm Max.
Dusting	Visual	Uniform	Uniform	Uniform	Uniform

**NOTE:**

- 1) Material is REACH Compliant.
- 2) We can produce material as per Mooney Viscosity requirement of customer at the time of dispatch.

### KEY APPLICATIONS

Applications	Auto Tyre	Tread Rubber	Moulded Goods	Cycle Tyres	Solid Tyres
Usage Recommendation (PHR) *	15	15	20	50	20

\* Based on GRP formulary / GRP internal working

Disclaimer: The information & data presented in this specification sheet are typical values and should not be considered as specifications. No warranty or guarantee expressed or implied is made regarding performance. The information and data are subject to change without prior intimation based on research and development work undertaken by the company.